


**SYSTEM : DEGADUR-MMA WITH COLOURED QUARTZ TEXTURED FINISH**



**METHOD STATEMENT**

**1. Surface Preparation**

- intensive roughening and cleaning by dust free and captive steel shot blasting using BLASTRAC machine.
- abrasive grinding by rotating tungsten carbide floor grinder at areas inaccessible to BLASTRAC machine.
- further cleaning by rotating steel brush and sand disc at plinths and corners.
- flame cleaning to remove moisture.
- vacuum clean to remove dirt and dust.

**2. Priming**

- apply DEGADUR floor sealer / 112 allowing good absorbency into open textured concrete.

**3. Coating**

- apply DEGADUR 418 base coat by hand trowel.
- broadcast coloured quartz onto wet base coat.
- to remove excess quartz by vacuum and brushing after the base coat have dried.
- to apply 2 transparent top coats to finish.