


SYSTEM : DEGADUR HIGH CHEMICAL RESISTANT WATERPROOFING & WEATHERPROOFING



METHOD STATEMENT

1. Surface Preparation

- intensive roughening and cleaning by dustfree and captive steel shot blasting using BLASTRAC machine.
- abrasive grinding by rotating tungsten carbide floor grinder at areas inaccessible to BLASTRAC machine.
- cleaning by rotating steel brush and sand dics to vertical surfaces/wall.
- flame cleaning to remove moisture.
- vacuum clean to remove dirt and dust.

2. Priming

- apply DEGADUR floor sealer / Primer B71.

3. Top Coating

- apply DEGADUR 418 base coat by hand trowel.
- apply DEGADUR 525 top coat to finish.

This application of DEGADUR TL is impervious, chemical resistant, waterproofing and weatherproofing. It has excellent stability against UV.